


## AMENDMENTS TO THE SPECIFICATION

Please amend the paragraph beginning on page 4, line 10, as follows:

The present invention B-component reactants include a novel polyol prepolymer chain extender that includes at least one amine reacted with an epoxy functional silicone. In one aspect of the present invention, the polyol prepolymer chain extender includes a silicone that has an epoxy end group which reacts with an aromatic or aliphatic amine or combination of aromatic and aliphatic amines to produce the novel polyol prepolymer chain extender. In one aspect of the present invention, the epoxy end group on the silicone is aliphatic and more preferably is glycidyl ether. The aliphatic epoxy end group provides increased UV and color stability of the silicone modified polyurea. Exemplary epoxy functional silicones include 2810 from OSI Specialties and SILRES<sup>®</sup> HP 1000 from Wacker Chemicals Corp. Both products have Hydrogen equivalent weights of 300-400. One non-limiting example of an epoxy functional silicone is shown in formula (I):

(I)



Application No. 10/648,934  
Amendment dated October 10, 2007  
Reply to Office Action Dated April 10, 2007

Docket No.: 009608.0113PTUS

wherein  $x$  is an integer from about 1 to about 20,  $y$  is an integer from about 1 to about 20, and  $z$  is an integer from about 1 to about 20.